

NP-SU SERIES

108

(Suede Base Plastisol Inks, Non-Phthalate)

Features

- Can express Suede, and Velvet effect.
- Mix 10~20% of <SM&SO SERIES> for colored effect.
- Mix <MT SEIRES> if more vivid color is needed.
- Matte finish, soft and non-tacky.

Application

- Use 110~150 t/in of mesh.
- Use higher mesh(higher than 130 t/in) for more effect.
- Can be mixed with <NP-SM&SO SERIES>.
- For Flash Cure, 5-10 sec / 392°F(200°C) is recommended, repeat several times if needed.
- Mix <#4900 FF BASE> for elongation and fast fusion. If you mix excessively, Suede effect can be reduced.

Remarks

- Stir before printing for convenient use.
- Excessive high temperature and long time may cause glossy surface and low Suede effect.
- Keep the proper temperature and time.
- Conduct cure thoroughly to do not loss adhesiveness and fastness.
- Conduct enough test before main printing.
- If needed to mix other product or material, contact AONE for more information.

Eco-Friendly

- Compliant with CPSIA(Pb, Phthalates).
- Meet standard of Eco-passport, adidas A-01.
- AONE's product does not contain six regulated materials, but we do not examine whole product. We recommend to examine every kind of regulated materials and pre-testing for your own use purpose.

Colors

4701 BASE

Method

- Substrates: 100% cotton, cotton blends, Polyesters.
- Mesh :110~150 t/in.
- Cure temp: 320°F (160°C), heating more than 60sec.
- Wash-up: mineral spirit, organic solvent.
- Caution: Do not dry clean, bleach or iron the printed area.

Packing & Storage

- Packaging: 20Kgs.
- Storage: Avoid strong Acidic compounds and direct sun keep in cool place(64~90°F / 18~32°C).